

1. **PRODUCT NAME:**
 CSS-1H
 SealMaster®/Hawaii
2. **CRUDE SOURCE:**
 Asphalt Hawaii
3. **MANUFACTURER:**
 SealMaster®/Hawaii
 2927 Mokumoa Street
 Honolulu, HI 96819-4404
 Phone: (808) 839-2782
 Fax: (808) 839-2002
 www.sealmasterhawaii.com

METHOD	TEST	MIN	MAX
T-59/D-6933 *	Sieve, %	...	0.10
T-59/D-6934 *	Residue, %	57	...
T-72/D-88	Viscosity, SFS @ 77°F.	20	100
T-59/D-6930 *	Storage Stability, 24-h, %	...	1.0
T-59/D-6935 *	Cement Mixing, %	...	2.0
T-59/D-7402 *	Particle Charge Test		Positive
TESTS ON RESIDUE:			
T-49/D-5	Penetration, 0.1mm	40	90
T-51/D-113	Ductility, cm	40	...
T-44/D-2042	Solubility, %	97.5	...

* Formerly part of ASTM D-244

This document shall not be reproduced except in full, without the approval of SealMaster.

The above tests meet AASHTO M-208 and ASTM D2397 Requirements for Cationic Emulsified Asphalt, and conform to Hawaii Emulsion Specifications.

SealMaster warrants that Product meets the chemical composition and performance requirements set forth in Technical Data. Liability to the buyer or user of this product is limited to the replacement value of the product only.

Copyright © 2011, SealMaster
 All Rights Reserved.

SealMaster/Hawaii
 Phone: (808) 839-2782
 www.sealmasterhawaii.com