

1. PRODUCT NAME

Plasti-Pave
Pavement Rejuvenator

2. MANUFACTURER

SealMaster®/Hawaii
2927 Mokumoa Street
Honolulu, HI 96819-4404
Phone: (808) 839-2782
Fax: (808) 839-2002
www.sealmasterhawaii.com

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit website at www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS

Plasti-Pave is an acrylic reinforced asphalt emulsion pavement sealer and rejuvenator designed to preserve and protect as well as beautify pavement surfaces.

Plasti-Pave replenishes the binder that is lost through oxidation, weathering and aging providing a "like-new" black appearance.

Plasti-Pave protects against oxidation, weathering, aging, moisture, UV and chemical attack.

Basic Uses: Ideal for use on roads, streets, airports, and highway shoulders. Not recommended for driveways or parking lots.

Composition: Polymer, Asphalt, Water, Surfactants and Emulsifiers.

Sizes: Available in tank wagons, totes, drums, and pails.

Color: Dries Black.

Limitations: Plasti-Pave shall not be applied when temperature is expected to drop below 50°F within a 24 hour period after application.

4. INSTALLATION

Surface must be cleaned of dirt and debris.

Methods: Plasti-Pave can be applied by spray or brush.

Application: For best results apply by spray or brush application.

Application Rate: Apply Plasti-Pave at a rate of 60-100 square feet per gallon.

Precautions: Both surface and ambient temperature shall be a minimum of 50°F. Temperature shall not drop below 50°F in a 24 hour period following application. Keep Out Of Reach Of Children. Do not store unopened containers in freezing temperatures.

5. AVAILABILITY & COST

Availability: Plasti-Pave Pavement Rejuvenator is supported by a national network of SealMaster facilities along with a national network of professional applicators.

Cost: Cost information can be obtained from a local applicator. Contact SealMaster for the representative in your area.

6. WARRANTY

SealMaster warrants that Plasti-Pave Pavement Rejuvenator meets the chemical composition and performance requirements set forth in section 4. Liability to the buyer or user of this product is limited to the replacement value of the product only.

7. TECHNICAL SERVICES

Manufacturer: Complete product specifications, material safety data sheets, and technical assistance is available from SealMaster.

Professional Applicators: Your local applicator is available to provide on-site inspections and recommendations to meet your specific needs.

9. FILING SYSTEMS

- SealMaster Online Specifications at www.sealmaster.net
- Complete SealMaster Product and Equipment Catalog Available

The statements made on this specification sheet are believed to be true and accurate and are intended to provide a guide for approved application practices. As workman-ship, weather, construction, condition of pavement, tools utilized, and other variables affecting results are all beyond our control, the manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. The manufacturer expressly disclaims any implied warranties of merchantability or fitness for a particular purpose. Warranty is void on multi-coat applications if material made by other manufacturers is used with this product.

Form No.: SMT-312
Revised: 1/13

Copyright © 2013, SealMaster
All rights reserved.

SealMaster/Hawaii
Phone: (808) 839-2782

www.sealmasterhawaii.com

Chemical & Physical Analysis

Tests On Emulsion:

| | |
|--|----------|
| Viscosity, Saybolt Furol at 77°F (25°C), s | 36 |
| Storage Stability Test, 24-h, %..... | 1 |
| Cement Mixing Test, %..... | < 2% |
| Sieve Test, %..... | 0.013 |
| Residue by distillation, %..... | 65% ± 2% |
| Copolymer %..... | 15% |

Test On Residue:

| | |
|---|--|
| Ductility, 77°F (25°C) 5 cm/min, cm | 40 min |
| Durability @ 750 hrs..... | No cracking, checking, blistering, or peeling. |